

Process and composition for preparing abrasion-resistant articles.

| | |
|---------------------|---|
| Patent Number: | <input type="checkbox"/> EP0358011, A3, B1 |
| Publication date: | 1990-03-14 |
| Inventor(s): | SCHMIDT HELMUT DR; HOFMANN KLAUS; KAISER ALFRED DR; PHILIPP GOTTFRIED DR; SEIFERLING BERNHARD |
| Applicant(s): | FRAUNHOFER GES FORSCHUNG (DE) |
| Requested Patent: | <input type="checkbox"/> DE3828098 |
| Application | EP19890115196 19890817 |
| Priority Number(s): | DE19883828098 19880818 |
| IPC Classification: | C08G77/58; C09D183/14 |
| ECC Classification: | C08G77/58, C09D183/14 |
| Equivalents: | ES2084592T, <input type="checkbox"/> JP2160836 |
| Cited Documents: | US4434103; EP0171493; US4073967; JP52114628 |

Abstract

To prepare scratchproof materials, a composition obtained by hydrolytic polycondensation of at least one aluminium compound, at least one organofunctional silane and, if desired, one or more inorganic oxide components, is applied to a substrate or subjected to a shaping process, after which it is cured, for example by heating.

Data supplied from the esp@cenet database - I2